

## DESCRIPTION

**TIMINOVA** is a water-based paint of a vinylic copolymer, selected loads and pigments, providing high quality finishes and decorative beauty with matt look in a selected range of colours **NCS** catalogue. It is suitable for all types of interior and exterior walls, on the most varied type of substrates, plaster sanded and smooth, concrete, cement, brick, synthetic stuccos, tinned and others, in new paintings or repainting of conventional smooth plastic paints, non-glosses.

## PROPERTIES

- Good coverage and whiteness
- Reasonable capacity of resistance to wet and dry polishing
- Colours that have great lightfastness and weatherfastness
- Good applicability
- Anti-Spatter

## PHYSICAL DATA

<b>COLOUR</b>		<b>S 0550-Y70R – S 0570-Y50R – S 0540-G40Y</b>
<b>FILM ASPECT</b>	Gloss	Matt
<b>SPECIFIC GRAVITY</b>		1.570 ± 0.050 g/cm <sup>3</sup>
<b>VISCOSITY</b>		80 - 90 KU
<b>SOLIDS BY WEIGHT</b>		60 % – Theoretical value

## APPLICATION DATA

### SURFACE PREPARATION

All surfaces must be dry, firm, free of grease, dust and other contaminants.

**New surfaces** – Over friable or dusty surfaces, after brushing, apply a coat of **Timisolador Acrílico Branco**. Over alkaline surfaces, apply a coat of **Timisolador Acrílico Incolor**. Over plasterboard and projected stucco, apply a coat of **Primário Praitmicryl** or **Timisolante Aquoso Branco**.

### Previously painted surfaces

**Indoors** – Brush to remove non-adherent old loose paint; repair damaged areas with **Massa Timifendas** and remove grease and dust.

**Outdoors** – Perform a wash with the aid of a under pressure water jet and let dry; repair damaged areas and proceed as for new surfaces. If the previous paint is chalky, apply one coat of **Timisolador Acrílico Incolor**.

**Previously lime washed surfaces** – Brush carefully. If possible wash down with the aid of a under pressure water jet, let dry and apply a coat of **Primário Acrílico Incolor**.

**New cement renders** – Wait for complete cement cure, which takes approximately 28 days. The cement rendering must be dry, firm, clean, free of grease, dust and other contaminants. Brush if needed, to remove non-adherent loose particles. Apply a coat of **Primário Praitmicryl** or **Timisolante Aquoso Branco** and let it dry.

**Previously painted cement renders** – Clean up the area with the aid of a under pressure water jet, brush to remove non-adherent old loose paint. Repair damaged areas and cracks with dimensions between 0,3 and 1,0 mm. In the areas where the cement renders are displayed proceed as indicated as the above line “new cement renders”.

This technical data sheet is merely of an advisory nature, based on current technical know-how, for guidance, and may be changed without prior notice. As the conditions of application are beyond our control, the company cannot under any circumstances be held responsible for the obtained final results in its use.

## APPLICATION CHARACTERISTICS

<b>APPLICATION METHOD</b>	Brush, anti-spatter roller and spray
<b>THEORETICAL COVERAGE</b>	10 to 12 m <sup>2</sup> /L/Per coat
<b>DRYING TIME</b>	Touch dry – 1 at 2 hours Repainting – 6 at 8 hours
<b>THINNING</b>	Thin the first coat with 10 % water and subsequent coats with 5% water
<b>APPLICATION</b>	Apply two coats of <b>Timinova</b>
<b>UTENSILS/TOOLS CLEANING</b>	The utensils/tools must be cleaned with water immediately after the application.

## ENVIRONMENTAL CONDITIONS DURING APPLICATION

Ambient Temperature	≥ 5 °C
Relative Humidity	≤ 90 %
Surface temperature	2 to 3 °C above dew point

## SHELF LIFE

When stored inside in original containers and sheltered from sunlight and cold at temperatures between 5 and 40 °C, the product has a shelf life of 3 years after its date of manufacture.

## OBSERVATIONS

When the paint is applied in places where due to environmental conditions, the possibility of attack of fungus or algae is foreseen, the addition of Antifungal and algae Additive is recommended until maximum 5%.

## HEALTH, SAFETY AND ENVIRONMENT

In general, avoid contact with eyes and skin; gloves, goggles and appropriate clothing must be worn. Keep out of the reach of children. Use only in well ventilated areas. Do not empty into drains. Keep the container properly sealed and stored in the correct place. Take correct measures when transporting the product; Prevent any accident or incident that may occur during transportation, in particular the rupture or deterioration of the packaging. Ensure that the container is correctly stacked in a safe area. Do not store or use the product in extreme temperature conditions always between 5 and 40 °C. Always take account of the appropriate legislation relating to the Environment, Hygiene, Health and Safety at Work. For more information it is essential to read the label on the container and the product Material Safe Data Sheet.

This technical data sheet is merely of an advisory nature, based on current technical know-how, for guidance, and may be changed without prior notice. As the conditions of application are beyond our control, the company cannot under any circumstances be held responsible for the obtained final results in its use.